

Test Report No. AJFS2204002786FF Date: JUN.16, 2022 Page 1 of 3

### **GUANGDONG BOSHUN BELTING CO., LTD.**

TWELVE RIDGE, YANGQIAO VILLAGE, BOLUO COUNTY, HUIZHOU CITY, GUANGDONG, CHINA

**Sample Description: PVC CONVEYOR BELT** 

SGS Ref No.: 15945661

Style/Item No.: /

The above sample(s) was / were submitted and identified on behalf of the client. SGS is not responsible for the authenticity, integrity and results of the data and information and / or the validity of the conclusion arising therefrom. Results apply to the sample as received.

\*\*\*\*\*\*

### **Test Requested:**

ISO 340:2013 Conveyor belts - Laboratory scale flammability characteristics - Requirements and test method.

Test Results: -- See attached sheet --

**Conclusion:** According to the test results, the specimen without covers **meets** the requirements of ISO 340:2013.

### **Test Period:**

Sample Receiving Date : APR.22, 2022

Test Performing Date : APR.22, 2022 TO APR.27, 2022

Signed for and on behalf of

SGS-CSTC Standards Technical Services Co., Ltd. Anji Branch



Approved Signatory



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.apx">http://www.sgs.com/en/Terms-and-Conditions.apx</a> and, for electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditio



# **Test Report**

No. AJFS2204002786FF

Date: JUN.16, 2022

Page 2 of 3

#### I. Test conducted

This test was performed in accordance with ISO 340:2013 Conveyor belts - Laboratory scale flammability characteristics - Requirements and test method.

### II. Sample details

| Sample description / Color | PVC conveyor belt (provided by client) / Black |
|----------------------------|--|
| Specimen size              | Length: 200mm; Width: 25mm; Thickness: 1mm     |

## Conditioning:

Before the test, the specimens shall be conditioned to constant mass at a temperature of  $(23 \pm 2)$  °C and a relative humidity of  $(50 \pm 5)$  % in accordance with ISO 18573.

#### III. Test results

Specimen without covers

| Items  | Longitudinal direction |    |    | Transverse direction |    |    |
|--|------------------------|----|----|----------------------|----|----|
| items  | 1                      | 2  | 3  | 4                    | 5  | 6  |
| Weather the specimen continues to flame after removal of the burner  | No                     | No | No | No                   | No | No |
| Afterflame time (s)  | 0                      | 0  | 0  | 0                    | 0  | 0  |
| Total duration of afterflame for each of the series of six tests (s) | 0                      |    |    |                      |    |    |
| Weather the flame re-appears   | No                     | No | No | No                   | No | No |
| Duration of the re-flame (s)   | 0                      | 0  | 0  | 0                    | 0  | 0  |

### Requirements:

1. Periods of afterflame (after removal of the burner)

The sum of the periods of flame for each of the series of six tests shall be less than 45 s and no individual value shall be greater than 15 s.

2. Non-reappearance of flame (after applying a current of air)

The flame shall not re-appear.

**Statement:** This declaration of conformity is only based on the result of this laboratory activity, the impact of the uncertainty of the results was not included.

**Remark:** The test method is not in CMA accredited scope. The test report shall only be used for client internal reference.

To be continued...



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.apx">http://www.sgs.com/en/Terms-and-Conditions.apx</a> and, for electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-and-Conditio



# **Test Report**

No. AJFS2204002786FF

Date: JUN.16, 2022

Page 3 of 3

## **Photo Appendix:**



SGS authenticate the photo on original report only

\*\*\* End of Report \*\*\*



Unless otherwise agreed in writing, this document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <a href="http://www.sgs.com/en/Terms-and-Conditions.aspx">http://www.sgs.com/en/Terms-and-Conditions.aspx</a> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <a href="http://www.sgs.com/en/Terms-and-Conditions/Terms-a-Document.aspx">http://www.sgs.com/en/Terms-and-Conditions/Terms-a-Document.aspx</a>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this advised that information contained hereon reflects the Company's findings at the time of its intervention only ad within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company, Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) are retained for 30 days only.

Attention:To check the authenticity of testing / inspection report & certificate, please contact us at telephone:(86-755) 8307

No. 301, Sunlight Road, 2 Block, Sunlight Industry Zone, Anji County, Zhejjang Province, China 313300 t (86-572) 5018825 f (86-572) 5018829 www.sgsgroup.com.cn 中国・浙江・安吉县阳光工业园二区阳光大道301号 邮编:313300 t (86-572) 5018825 f (86-572) 5018829 e sgs.china@sgs.com